

**TECHNICAL DATA SHEET**

Revision date: 08.09.2020

**GUARD TRUCK BED LINER TINTABLE**

- Article number:** 37416
- Intended use:** Car refinishing Product/ Paint
- Product description:** Highly resistant 2K polyurethane-acrylic paint for a scratch-resistant, robust and tintable coating of truck bed surfaces (e.g. Pick-Up truck beds) and all heavy duty surfaces on commercial vehicles, off-road vehicles, camping cars, trailers, SUVs etc.
- Possible application areas:**
- bodies of SUVs and off-road vehicles
  - rims of SUVs and off-road vehicles
  - floors and storage areas in caravans
  - underbodies and chassis
  - bullbars, running boards, roof racks, spare wheel covers and so on.
  - fender well
  - access ramps, decks of recovery vehicles and trailers
- General qualities:** Beside its very high wear resistance Guard Truck Bed Liner Tintable also provides an excellent mechanical and chemical resistance. The excellent vertical stability enables the user to apply extremely high-build coatings. Easy to use as 750 ml Guard Truck Bed Liner Tintable is pre-filled in a 1 litre can for underbody sealants. Just add 250 ml Chamäleon Hardener for Guard Truck Bed Liner, shake the can vigorously, add the colouring material (paint), shake the can vigorously again and apply the mixture using an underbody sealant spray gun.
- Properties:**
- high UV and weathering resistance
  - excellent shock and scratch resistance
  - high resistance to fuels and oils
  - excellent water resistance
  - provides noise reduction
  - short-term temperature exposure: 180 °C
  - permanent temperature exposure: 150 °C
- Spreading rate: 3 m<sup>2</sup>/l for 200 µm dry film thickness

## Processing instructions:

**Colour:** Base Coat or Mix-System

**Mixing ratio:** by volume lacquer: hardener

3 : 1 or

750 ml Guard Truck Bed Liner Tintable in 1,1 litre cans for underbody sealants +  
250 ml Chamäleon Hardener for Guard Truck Bed Liner + approx. 2 minutes  
shaking

**Hardener:** Hardener for Guard Truck Bed Liner

**Pot life:** 1 - 1,5 h at 20 °C

### Mixing/ tinting procedure for applications with underbody sealant spray gun (UBS)

1. Shake the closed can with Chamäleon Guard Truck Bed Liner Tintable vigorously .
2. Open the can, add 250 ml hardener, close the can and shake vigorously for approx. 2 minutes.
3. Open the can, add 100 ml *undiluted* Base Coat and shake vigorously for approx. 2 minutes

### Mixing/ tinting procedure for applications with gravity spray guns (complete set)

1. Shake the closed can with Chamäleon Guard Truck Bed Liner Tintable vigorously.
2. Pour 750 ml Guard in a mixing cup, add 250 ml hardener and mix thoroughly.
3. Add 100 ml Base Coat plus thinner and mix thoroughly.

### Mixing/ tinting procedure for applications with gravity spray guns (smaller amounts)

1. Shake the closed can with Chamäleon Guard Truck Bed Liner Tintable vigorously .
2. Pour a small amount of Guard in a mixing cup, add the hardener in a mixing ratio of 3 : 1 by volume and mix thoroughly.
3. Add 10 % by (volume) of Base Coat plus thinner and mix thoroughly.

**Now the mixture is ready for use!**

**Thinner:** Chamäleon Thinner

**Spray viscosity:**


**Gravity**

See application mode

**UBS spray gun**

undiluted

## Application mode:

	Application mode	Nozzle (mm)	Dilution	How to apply a rough texture
	UBS-spray gun	-	-	<ol style="list-style-type: none"> <li>1. Apply a uniform coat with a pressure setting of 3 - 4 bar until full coverage is achieved.</li> <li>2. Observe flash-off time of between 10 minutes and 1 h.</li> <li>3. To achieve the desired texture reduce the pressure to 1 - 1,5 bar and increase the spray distance to approx. 45 - 60 cm.</li> </ol>

	HVLP (low pressure)	2,5	10 %	<ol style="list-style-type: none"> <li>1. Apply a uniform coat with a pressure setting of 2 bar until full coverage is achieved.</li> <li>2. Observe flash-off time of between 10 min and 1 h.</li> <li>3. To achieve the desired texture reduce the pressure to approx. 1 bar and increase the spray distance to approx. 40 - 50 cm.</li> </ol>
	UBS-spray gun	-	-	<ol style="list-style-type: none"> <li>1. Apply a uniform coat with a pressure setting of 3- 4 bar until full coverage is achieved.</li> <li>2. Observe flash-off time between of 10 min and 1 h.</li> <li>3. To achieve the desired texture reduce the pressure to approx. 2 bar und increase the spray distance to approx. 45 - 60 cm.</li> </ol>
	HVLP (low pressure)	2,0 - 2,5	15 %	<ol style="list-style-type: none"> <li>1. Apply a uniform coat with a pressure setting of 2 bar until full coverage is achieved</li> <li>2. Observe a flash-off time between of 10 min and 1 h.</li> <li>3. To achieve the desired texture reduce the pressure to approx. 1,5 bar and increase the spray distance to approx. 45 - 60 cm.</li> </ol>
	UBS-spray gun	-	-	<ol style="list-style-type: none"> <li>1. Apply a uniform coat with a pressure setting of 3 - 4 bar until full coverage is achieved.</li> <li>2. Observe flash-off time of between 10 min and 1 h.</li> <li>3. To achieve the desired texture, set the pressure to 3 - 4 bar and increase the spray distance to approx. 90 cm.</li> </ol>
	HVLP (low pressure)	1,6 - 1,8	20 %	<ol style="list-style-type: none"> <li>1. Apply a uniform coat with a pressure setting of 2 bar until full coverage is achieved.</li> <li>2. Observe flash-off time of between 10 min and 1 h.</li> <li>3. To achieve the desired texture increase the spray distance to approx. 60 cm.</li> </ol>

**Flash-off time:**

Between the coats: 5 - 8 min  
Prior to oven drying: 10 - 15 min

**Dry film thickness:**

100 - 380 µm

**Drying time:**

Object temperature	Dust dry	Set to touch	Ready for assembly	Sandable	Recoatable
20 °C	15 - 20 min	3 - 4 h	24 h	-	-
60 °C	-	30 min	1 - 2 h	-	-

Fully cured after 7 days (at 20 °C).

**Storage:** at least 3 years in unopened original container.

**VOC regulation:**

EU limit value: Category A/j 500 g/l - B/e 840 g/l  
This product contains max. 500 g/l of VOC.

**Processing conditions:**

Please only use in an adequately ventilated environment with an ample supply of fresh air. Processing temperature should be at least + 10 C° and max. air humidity should not exceed 80%.

**Substrate preparation:**

On all surfaces except old paint layers, a primer must be used. All surfaces must be clean, dust and fet/oil free. Sand slightly if necessary (remove any rust and mill scale) and degrease with Silicone remover.

**steel:**

priming coat: suitable Chamäleon 1K and 2K primer and filler (e. g. Chamäleon 1K-Primer fast, Chamäleon Washprimer 2:1, Chamäleon Acrylic primer 488, Chamäleon 2K Epoxy primer)  
finishing coat: Chamäleon Guard Truck Bed Liner Tintable (coat thickness: 100 - 380 µm)

**zinc and aluminium:**

priming coat: suitable Chamäleon 1K and 2K primer and filler (e. g. Chamäleon Washprimer 2:1, Chamäleon Acrylic primer 488, Chamäleon 2K Epoxy primer)  
finishing coat: Chamäleon Guard Truck Bed Liner Tintable (coat thickness: 100 - 380 µm)

**wooden substrates:**

priming coat: Chamäleon 2K Epoxy primer

finishing coat: Chamäleon Guard Truck Bed Liner Tintable (coat thickness: 100 - 380 µm)

**GRP and sound 2K-resistant old paintworks:**

finishing coat: Chamäleon Guard Truck Bed Liner Tintable (coat thickness: 100 - 380 µm)

or with priming coat, if irregularities must be levelled:

priming coat: Chamäleon Primer 488 or 466

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via:  
[info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)

For safety information, please refer to the corresponding Safety Data Sheet.