



H69 PLUS VANTIX UHS CLEAR

UHS 2K Acrylic Clearcoat

Innovative clearcoat whose rheological properties give it notable resistance to sagging whilst ensuring excellent flow. Other main features include ease of application and high gloss which give the product a high level final quality. Particularly suitable for self-repair cycles with water-based matt basecoats where it allows the effects due to absorption to be significantly reduced.

The maximum VOC value for this product in the ready-to-use form (belonging to sub-category IIB(d)) is 420 g/l, in accordance with 2004/42 Regulation.

B) TECHNICAL DATA:

Composition	Hydroxylated acrylic resins
Specific weight	0,975 ± 0,030 kg/l
Available colours	Colourless, transparent
Safety data	Refer to the safety data sheet

C) SURFACE PREPARATION :



* Matt base coat for two coats of solvent-based paint

* Matt base coat for two coats of water-based paint

D) CAUTIONS:

- * Mix well before use.
- * Comply with the application ratios.
- * Do not use the product at temperatures below 10°C.
- * Keep in a cool, dry place.



E) PROCESSING:



2:1 with C63/C67/C68 Hardener, potlife 60'-90' at 20°C.



Do not dilute.
18-20" DIN 4 at 20°C.



1,3-1,4 mm 2,0-2,5 bar
Apply a light coat followed by a full coat to obtain a final dry thickness of 50 – 60 micron.



5'-10'



at 20°C : Drying Time : 4-6 h. Buffing Time: 15-16 h
at 60°C : Drying Time : 25'. Buffing Time : 30' after cooling.



10' at 1 mt.

F) TOOLS CLEANING:

* With thinner for polyurethanic products

G) RECOATING :

Technical indications and advices are based on our own experiences. We assure the perfect quality of products. However, being the utilization out of our control, we assume no responsibility on the results obtained