



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

## TECHNICAL DATA SHEET

### CHAMÄLEON BUMPER SPRAY

<b>Article number:</b>	<b>26314 (Grey), 26334 (Black)</b>
<b>Intended use:</b>	Car refinishing Product/ Preparation
<b>General characteristics:</b>	High quality bumper spray to repair and embellish plastic bumpers, maintaining the original bumper structure.
<b>Product characteristics:</b>	<ul style="list-style-type: none"><li>• Excelent coverage</li><li>• Lasting colour and lasting gloss</li><li>• Scratch free and shock proof</li><li>• Resistant to chemicals and weather influences</li><li>• Excellent adhesion</li><li>• Maintains the original structure of the bumper</li></ul>

#### Physical and Chemical

Contents  
Base  
VOC-content  
Solid content  
Gloss  
Coverage  
Dust dry  
Tack free  
Hardened/resprayable  
Heat resistant

#### Characteristics

400 ml  
Alkyd resin  
Approximately 84% w/w  
Approximately 16% w/w  
Satin matt  
Two bumpers  
After 20 to 30 minutes  
After 1 hour  
After 24 hours  
To 110 °C

#### Usage:

Before use, carefully read the directions on the packaging and act accordingly.

#### Pre Treatment:

The surface should be clean, dry and free of grease.



Chamäleon GmbH  
Rudolf-Diesel-Straße, 8a  
69115 Heidelberg-Germany  
Tel.: +49-(0)-6221 520440  
Fax: +49-(0)-6221 520449  
E-mail: [info@chamaeleon/produktion.de](mailto:info@chamaeleon/produktion.de)  
<http://www.chamaeleon/produktion.de>

**Treatment:**

The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the bumper spray in several thin layers, till the desired result has been achieved. Before applying the next layer, again shake the aerosol.

**After use:**

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

*For the additional information that is not included to the Technical Data Sheet apply to the supplier:  
e-mail: [info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)  
See information on safety in Safety Data Sheet.*