

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 15.02.2023

TECHNICAL DATA SHEET

PLASTIC PRIMER

Article number: 26014

Colour: transparent

Intended use: Car refinishing product/ Preparation

General characteristics: High quality, fast drying plastic primer to treat surfaces,

treated and untreated, of several types of plastic.

Quality and properties:

Fast drying

Excellent adhesion

Re-sprayable with all lacquer systems

Physical and chemical characteristics:

Base: Polyolefine resin

VOC-content: Approximately 99 % w/w **Solid content**: Approximately 1 % w/w

Application process:

Before use, carefully read the directions on the packaging and act accordingly

Pre treatment:

The surface should be clean, dry and free of grease. When desired, slightly sand the surface, grain 600.

Treatment:

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 cm.

Spraying operations	DFT	Consumption
max. 2 thin layers	-	2 - 3 m ²

Flash-off time	Between the coatings	Before the oven drying
	2 - 3 min.	-



CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

Drying	Dust dry	Recoatable
	-	10 - 15 min.

After use:

After drying, without sanding, re-sprayable with all lacquer systems. After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical data sheet, please contact the supplier under: e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding Safety data sheet.