

CHAMÄLEON GMBH RUDOLF-DIESEL-STRASSE 8A 69115 HEIDELBERG GERMANY

FON 0049 (0) 6221 - 520 440 FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Revision date: 04.01.2019

TECHNICAL DATA SHEET

RUST CONVERTER PRIMER

Article number: 26060 **Colour:** Transparent Intended use: Car refinishing product/ Protective coating General information: Rust converter primer is an epoxy-resin based anticorrosion coating. It converts rust into a protective layer which also acts as a primer. Once fully cured (12 - 24 hours) the rust is neutralized and the surface can be re-coated. Surfaces: Suitable for sheet metal, ferous metal, steel **Characteristics:** Rust is neutralized and chemically converted

- Combats corrosion. Suitable for the effective treatment and prevention of rust
- Long-term protection against corrosion and acts as a primer in one operation
- Durable protective coating

Application process:

Pretreatment / Cleansing:

Remove loose rust, dirt and grease Pre-cleansing using Silicone remover

Preparation: Shake can vigorously until the mixing balls moves freely!

Application: Spray to test.

Spraying distance approx. 20 - 25 cm

3 - 4 coat - allowing the product to dry in between each coating

Flash-off time: 3 - 5 min. between each coating

After use: Turn can upside down and spray until the valve is clean, this prevents the valve from clogging up.

Chamäleon GmbH – Technical Data Sheet



69115 HEIDELBERG GERMANY FON 0049 (0) 6221 - 520 440

RUDOLF-DIESEL-STRASSE 8A

CHAMÄLEON GMBH

FAX 0049 (0) 6221 - 520 449

MAIL INFO@CHAMAELEON-PRODUKTION.DE WEB WWW.CHAMAELEON-PRODUKTION.DE

Processing conditions:

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +15 °C and max. air humidity should not exceed 65%.

Drying	Set to touch	Recoatable
	12 - 24 h	24 h

Storage:

In tightly closed original containers at least 10 years shelf life

VOC regulation:

EC limiting value for the product (cat. B/e): 840 g/l (2007) This product contains a maximum of 625 g/l VOC [5.22 lbs/gal]

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under: e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.