

TECHNICAL DATA SHEET*Revision date: 27.04.2021***ACRYLIC AEROSOLS**

Article number:	26204 (black matt), 26205 (black semimatt), 26206 (white matt), 26214 (black glossy) 26414 (white glossy)
Colour:	Black, white
Intended use:	Car refinishing product/ Clear coating material, Varnish
General characteristics:	For the treatment of surfaces, treated and untreated, of wood, metal, aluminium, glass, stone and various types of plastic.
Product characteristics:	<ul style="list-style-type: none">▪ Fast drying▪ Good coverage▪ Non-fading and UV resistant▪ Good surface hardness▪ Resistant to petrol, chemicals and weather influences▪ Wear resistant and scratch free▪ Excellent adhesion
Physical and chemical properties:	
Contents:	500 ml
Base:	Acrylic resin
Gloss:	High gloss/Matt/Semimatt
VOC-content:	Approximately 91% w/w
Solid Content:	Approximately 9% w/w
Coverage:	1,5 to 2 m ²
Dust dry:	After 5 to 10 minutes
Tack free:	After 10 to 20 minutes
Hardened/re-sprayable:	After 2 hours
Heat resistant:	To 110°C

Application process:

Before use, carefully read the directions on the packaging and act accordingly



CHAMÄLEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAMÄLEON GMBH
RUDOLF-DIESEL-STRASSE 8A
69115 HEIDELBERG
GERMANY

FON 0049 (0) 6221 - 520 440
FAX 0049 (0) 6221 - 520 449
MAIL INFO@CHAMAELEON-PRODUKTION.DE
WEB WWW.CHAMAELEON-PRODUKTION.DE

■ **Processing conditions:**

Please only use in an adequate ventilated environment with an ample supply of fresh air. Processing temperature should be at least +10 °C and max. air humidity should not exceed 80%.

Pre Treatment: The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface. Apply a layer of Chamaeleon Spray Primer suitable for the surface. After drying, sand the base layer (grain 600).

Treat: The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimeters. Apply the lacquer in several thin layers. Before applying the next layer, again shake the aerosol.

After use: Clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this technical data sheet, please contact the supplier under:

e-mail: info@chamaeleon-produktion.de

For safety information, please refer to the corresponding safety data sheet.

STEUERNUMMER/TAX NR.: DE 231468544
EORI NR./CUSTOMS NR.: DE 6029442 / HRB 9778
GESCHÄFTSFÜHRER/CEO: SASCHA HAGEMANN

BANK HEIDELBERGER VOLKSBANK EG
IBAN DE78 6729 0000 0042 8627 03
BIC GENODE61HDI