



CHAM'ALEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAM'ALEON GMBH  
RUDOLF-DIESEL-STRASSE 8A  
69115 HEIDELBERG  
GERMANY

FON 0049 (0) 6221 - 520 440  
FAX 0049 (0) 6221 - 520 449  
MAIL INFO@CHAMAELEON-PRODUKTION.DE  
WEB WWW.CHAMAELEON-PRODUKTION.DE

## ***TECHNICAL DATA SHEET***

### **CHAM'ALEON SPRAY PUTTY**

<b>Article number:</b>	<b>26701</b>
<b>Intended use:</b>	Car refinishing Product/ Preparation
<b>General characteristics:</b>	High quality, fast-drying filler to fill small irregularities in surfaces, treated and untreated, of wood, metal and aluminum. Suitable primer as pre treatment for re-spraying with all lacquer systems (alkyd resin, nitro cellulose, 1-K acrylic and 2-K acrylic lacquers).
<b>Product characteristics:</b>	<ul style="list-style-type: none"><li>• Fast drying</li><li>• Excellent coverage</li><li>• Corrosion preventive</li><li>• Easy to sand, both wet and dry (from grain 400)</li><li>• Excellent filling property</li><li>• Good adhesion</li><li>• Re-sprayable with all lacquer systems</li></ul>

#### **Physical and Chemical**

Contents  
Base  
Colour  
VOC-content  
Solid content  
Gloss  
Coverage  
Dust dry  
Tack free  
Hardened/resprayable  
Heat resistant

#### **Characteristics**

400 ml  
Acrylic resin  
Beige-yellow  
Approximately 75% w/w  
Approximately 25% w/w  
Satin matt  
1,25 to 1,75 m<sup>2</sup>  
After 5 to 10 minutes  
After 10 to 20 minutes  
After 2 hours  
To 110 °C

#### **Usage:**



CHAM'ALEON GMBH / RUDOLF-DIESEL-STRASSE 8A / 69115 HEIDELBERG / GERMANY

CHAM'ALEON GMBH  
RUDOLF-DIESEL-STRASSE 8A  
69115 HEIDELBERG  
GERMANY

FON 0049 (0) 6221 - 520 440  
FAX 0049 (0) 6221 - 520 449  
MAIL [INFO@CHAMAELEON-PRODUKTION.DE](mailto:INFO@CHAMAELEON-PRODUKTION.DE)  
WEB [WWW.CHAMAELEON-PRODUKTION.DE](http://WWW.CHAMAELEON-PRODUKTION.DE)

Before use, carefully read the directions on the packaging and act accordingly.

**Pre Treatment:**

The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.

**Treatment:**

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimeter.

Apply the filler in several thin layers. Before applying the next layer, again shake the aerosol.

**After use:**

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.

This release replaces all eventually earlier issued versions.

For additional information, not contained in this Technical Data Sheet, please contact the supplier via:  
[info@chamaeleon-produktion.de](mailto:info@chamaeleon-produktion.de)

For safety information, please refer to the corresponding Safety Data Sheet.